

电池级碳酸锂基准交割品

Li2CO3	磁性物质含量	水分含量	Na	Mg	Ca	K	Fe	Zn	Cu
≥99.5%	≤0.00003%	≤0.25%,	≤0.025%	≤0.008%	≤0.008%	≤0.005%	≤0.001%	≤0.0003%	≤0.0003%
Si	Al	Mn	Ni	SO4 2-	Cl	且烧失量1	B 2	F 3	Pb
≤0.003%	≤0.001%	≤0.0003%	≤0.001%	≤0.08%	≤0.005%	≤0.50%	≤0.005%	≤0.015%	≤0.0003%
粒 度 D10									
D10≥1μm	3μm≤D50≤8μm	9μm≤D90≤15μm							

注：其他有害物质不作要求

电池级碳酸锂替代交割品及升贴水：

Li2CO3	Na	Mg	Ca	K	Fe	SO42-	Cl	F	水分含量	盐酸不溶物4
≥99.2%	≤0.08%	≤0.015%	≤0.025%	≤0.02%	≤0.002%	≤0.20%	≤0.01%	≤0.03%	≤0.3%	≤0.005%

注：磁性物质含量、其他杂质、粒径和有害物质不作要求；

